



UNI EN 485-2 : 2013 (E)
Caratteristiche meccaniche

Serie 4000	Stato metallurgico	Rm MPa		Rp0,2 MPa		Allungamento, min. %	
		Min.	Max	Min	Max	A50 mm	A
4006 Al Si1Fe	F	95					
	O	95	130	40		da 17 a 25	
	H 12	120	160	90		da 4 a 5	
	H 14	140	180	120		3	